



## Colorants

# Linea ECO

Codice	Pigmento	C.I.	% indicativa	Viscosità (cps)	Peso spec.
1003	White	P.W. 6	72	5500 (± 1500)	2,11 ± 0,06
1010	Black 430	P.B. 7	42	3000 (± 1000)	1,24 ± 0,03
1011	Black OX	P.B. 11	60	8000 (± 2000)	1,85 ± 0,05
1020	Blue Alfa	P.B. 15:2	45	2500 (± 1000)	1,20 ± 0,05
1021	Blue Beta	P.B. 15:3	40	3000 (± 1000)	1,20 ± 0,05
1022	Blue 36	P.B. 36	67	9500 (± 2500)	2,00 ± 0,06
1030	Yellow OX	P.Y. 42	60	7000 (± 2000)	1,75 ± 0,05
1031	Yellow 154	P.Y. 154	36	7500 (± 2500)	1,15 ± 0,05
1032	Yellow 184	P.Y. 184	55	4500 (± 1500)	1,83 ± 0,05
1033	Yellow OX Dark	P.Y. 42	57	7500 (± 1500)	1,75 ± 0,05
1034	Yellow 3	P.Y. 3	46	2250 (± 750)	1,20 ± 0,05
1035	Yellow OX Bright	P.Y. 42	57	7000 (± 2000)	1,75 ± 0,05
1036	Yellow 74	P.Y. 74	46	4000 (± 1000)	1,14 ± 0,04
1040	Red OX	P.R. 101	58	6000 (± 2000)	1,90 ± 0,05
1042	Red 112	P.R. 112	46	3000 (± 1000)	1,14 ± 0,04
1046	Red 168	P.R. 168	34	3750 (± 1250)	1,18 ± 0,03
1047	Red OX Bright	P.R. 101	42	5000 (± 2000)	1,50 ± 0,04
1050	Brown	MIX	58	6000 (± 1000)	1,77 ± 0,05
1062	Orange 5	P.O. 5	46	3000 (± 1000)	1,20 ± 0,05
1064	Orange 36	P.O. 36	10	2500 (± 1000)	1,24 ± 0,05
1081	Violet 23	P.V. 23	20	1000 (± 500)	1,07 ± 0,07
1091	Green 7	P.G. 7	42	4000 (± 1000)	1,31 ± 0,05
1097	Green OX	P.G. 17	60	4500 (± 1500)	2,04 ± 0,06

#### GENERAL INFORMATIONS:

The Linea ECO pigments and dispersing system are studied to be used in waterbased paints, both for external and internal use, and in paints based on silicates, silicones (only when permitted by the pigment), etc...

The aim of Linea ECO is to supply pigments with a high resistance in external use, both in full tone and in shade. The use of Linea ECO makes possible to obtain a wide range of colours using the smallest possible quantity of surfactants in order to obtain better resistance performances.

Linea ECO has got the smallest V.O.C. as requested by the newest laws on environment protection; they can be easily used in tintometric systems, both manual and electronic ones, because these colorants are controlled by the colorimetric point of view and they do not form any sedimentation nor they block the pumps.

#### TECHNICAL DATA SHEET:

Look:	Fluid, pumpable and dosable pasta
Smell:	Very light, almost odourless.
pH (dispersion in water at 10%):	9,0 ± 1
Boiling point:	>100°C
Tone tolerance:	(CIELAB) DE < 1
Strenght tolerance:	± 3%
Attention:	mix before any use; close the packaging after use.

Via Marconi, 73 - 44100 Ferrara  
 Tel. +39.0532.773742 r.a. - Fax +39.0532.773596  
 e-mail: gfc@gfcchimica.com - www.gfcchimica.com

**COMPANY  
 WITH QUALITY SYSTEM  
 CERTIFIED BY DNV  
 =ISO 9001/2000=**